



Delivery Program Version: 4. April 2008	Silky Matt and Matt White Glass Colours Firing range 480°- 600° C	Page: 1/1
---	---	---------------------

Semitransparent to opaque Colours

Range of application:

Imitation of etching, Imitation of sandblasting, Lighting fixtures, Drinking glasses, Cosmetic glasses, Glass Bottles

Indication	Type Nr.	480° C	520° C	560° C	580° C
Matt Covering	B	matt	satin matt	satin gloss	gloss
Relief	No. 60	-	matt	satin matt	satin matt
Silky matt	F 9018	-	matt	satin matt	satin matt
Silky matt	F 9037	-	matt	matt	satin matt
Silky matt	F 9079	matt	matt	satin matt	satin matt
Silky matt	F 9098	-	matt	satin matt	satin matt
Silky matt	BG 9193 *	-	matt	satin matt	satin gloss
Gold Covering	F 9100	matt	satin matt	satin gloss	gloss
Gold Covering	F 9117	matt	satin matt	satin gloss	gloss
Silky matt	F 9155	-	matt	satin matt	satin matt
Matt white	F 9081	-	-	matt	matt
Matt white	F 9140	-	-	opaque matt	opaque matt
Matt white	F 9168	-	-	opaque matt	opaque matt
Matt white	F 9170/ W	-	opaque matt	satin matt	satin matt
Matt white	F 9178	-	-	opaque matt	opaque matt

* Leadfree

Screen: 120 T (threads / cm) polyester

Mixing ratio: colour powder 60 weight units
Media 40 weight units

Please Note:

The informations in this leaflet are based on our current knowledge and experience. This description does not release the users from examinations and tests of their own because of uncountable possible influences, when using and applying the products in connection with every other material being involved in the production. It can not be deduced a legally obliged assurance for specific characteristics or for the aptitude of a definite usage purpose. The receiver of our products has to observe by his own responsibility probable protecting rights as well as existing laws, rules and regulations.

Rüger & Günzel GmbH
Dornhofstrasse 71
D 63263 Neu-Isenburg
Tel: +49(0)6102-812940
Fax: +49(0)6102-8129440
E-Mail: info@rgfarben.de